



TEST REPORT

CheckCode:317483 Report No.:C202008111983E

DONGGUAN HUATUO SURFACE TECHNOLOGIES COMPANY LIMITED **Applicant:** Address: 302, NO.33 BUILDING, ZHONGHUI KIN'S PARK, HUANGJIANG TOWN,

DONGGUAN CITY, GUANGDONG

The following sample information was submitted and identified by/on the behalf of the client

Name: Instantaneous adhesive

Type/Model: HT460

Reference HT406, HT420, HT403, HT495, HT28630, HT401, HT768, 502

Type/Model:

Sample Type: α-cyanoacrylic body adhesive Sanitary materials and fibers Application area:

Sample State: Normal

Date of Receipt: Aug. 18, 2020 Test Period: Aug. 18, 2020 - Aug. 27, 2020

Test Request: Volatile organic compounds(VOCs) content

GB 33372-2020 Judge Standard:

Test Result: Please refer to following page(s).

Conclusion: Please refer to following page(s)

Reviewed by Approved by Edited by



Seal of GUANGZHOU GRG METROLOGY & TE Issue date: Aug. 27.

This test report is responsible for the tested samples only. Without permission of the test center this test report is not permitted to be duplicated in extracts. The test report is invalid without the specialized stamp of GUANGZHOU GRG METROLOGY & TEST CO., LTD. The test report is invalid if altered. Objections to the test report must be submitted to GUANGZHOU GRG METROLOGY & TEST CO., LTD. within 15 days.



TEST REPORT

CheckCode:317483 Report No.:C202008111983E

Sample description:

Sample No.	Description
1	Transparent liquid

Test results:

Volatile organic compounds(VOCs) content

Test Method: With reference to HG/T 2492-2018 Appendix B.

Test Item	Sample 1	Unit	MDL	Limit	Conclusion
Volatile organic compounds(VOCs)	35.9	g/kg	0.1	/	/

Remark: 1) MDL = method detection limit

2) The report is English version of test report C202008111983. In case of divergence, the Chinese text shall be regarded as authentic.







TEST REPORT

CheckCode:317483 Report No.:C202008111983E

Photo of Sample

-----End of Report-----

